



QUALITY MANAGEMENT SYSTEM

UR.13-SD-U40231.0

REVISION NO

PAGE

1

1/1

F2-26TO LOW DENSITY POLYETHYLENE PRODUCT SPECIFICATION

TRADE NAME : PETILEN F2-26TO

GUARANTEED VALUES :

<u>TESTS</u>	<u>UNIT</u>	<u>VALUE</u>	<u>METHOD</u>
Melt Flow Rate (MFR) (190°C / 2.16 kg)	g/10min	2.1 - 3.0	ASTM D-1238
Density,23°C	g/cm ³	0.924- 0.928	ASTM D-1505
Film Quality	-	A	ALKATHENE-36

TYPICAL VALUES :

Haze	%	6.3	ASTM D-1003
Gloss	-	78	ASTM D-2457
Ash	%wt	0.10	ALKATHENE 509

PRODUCT SHAPE : Pellets

PACKING : - In 25 kg FFS (Form Fill Seal) white colored PE bags
or 1400 kg big-bags
- Bulk loading to silobus or container (20 ft. or 40 ft.)

STORAGE CONDITIONS : In closed and dry areas, sheltered from direct sun light

APPLICATION : Material is particularly suitable for high speed automatic packaging film

MSDS NO : UR.13-BF-00007-ING

NOTE: Typical values are the average results of the analyses made in Petkim's laboratories, provided for information only. They are not guaranteed values.

GN - YS - FO - 00001