



QUALITY MANAGEMENT SYSTEM

UR.17-SD-U1731.0

REVISION NO

PAGE

7

1/1

EH 241 POLYPROPYLENE PRODUCT SPECIFICATION

TRADE NAME : PETOPL EN EH 241

GUARANTEED VALUES :

| TESTS | UNIT | VALUE | METHOD |
|---|---------|---------|-------------|
| Melt Flow Rate (MFR) (230°C / 2.16 kg) | g/10min | 20 - 28 | ASTM D-1238 |
| Contamination, 100 g | pcs | Max. 5 | TM-113 |

TYPICAL VALUES :

| | | | |
|--------------------------------|--------------------|-----|----------------|
| Tensile Strength - at Yield | kg/cm ² | 365 | ASTM D-638 |
| Colour, b-value (10D65) | - | 1.5 | Hunter Lab. CQ |

PRODUCT SHAPE : Pellets

PACKING : In 25 kg FFS (Form Fill Seal) white colored PE bags or 1400 kg big-bags

STORAGE CONDITIONS : In closed and dry areas, sheltered from direct sun light

APPLICATION : Suitable for very rapid injection moulding applications. General purpose injection and fibre grade. (plastic goods, toys, fibres)

MSDS NO : UR.17-BF-00015-ING

NOTE: Typical values are the average results of the analyses made in Petkim's laboratories, provided for information only. They are not guaranteed values.

PETOPL EN EH-241 has production permission certificate related to plastic materials and articles intended to come into contact with foodstuffs , dated 12.08.2013 and no. TR-35-K017539 given by Turkish RepublicFood-Agriculture and Livestock ministry

GN - YS - FO - 00001